

MONEL® nickel-copper alloy 400 (UNS N04400/W.Nr. 2.4360 and 2.4361) is a solid-solution alloy that can be hardened only by cold working. It has high strength and toughness over a wide temperature range and excellent resistance to many corrosive environments. Composition is shown in Table 1.

Alloy 400 is widely used in many fields, especially marine and chemical processing. Typical applications are valves and pumps; pump and propeller shafts; marine fixtures and fasteners; electrical and electronic components; springs; chemical processing equipment; gasoline and fresh water tanks; crude petroleum stills, process vessels and piping; boiler feedwater heaters and other heat exchangers; and deaerating heaters.

PHYSICAL CONSTANTS AND THERMAL PROPERTIES

The physical constants and thermal properties of MONEL alloy 400 are shown in Tables 2 and 3. The effect of temperature on modulus of elasticity in tension is in Figure 1.

It will be noted in Table 2 that the Curie temperature lies within the ambient range. It is affected by variations in chemical composition. The values shown represent the range which can be expected from normal production; therefore, some heats will be magnetic at room temperature and others not. If there is a strong requirement for nonmagnetic characteristics, other MONEL alloys should be considered.

Table 1 - Limiting Chemical Composition, %, of MONEL Alloy 400

Nickel (plus Cobalt)	63.0 min.
Carbon	0.3 max.
Manganese	2.0 max.
Iron	2.5 max.
Sulfur	0.024 max.
Silicon	0.5 max.
Copper	28.0 - 34.0

Table 2 - Physical Constants of MONEL Alloy 400^a

Density, g/cm ³	8.80
lb/in. ³	0.318
Melting Range, °F	2370-2460
°C	1300-1350
Modulus of Elasticity, 10 ³ ksi	
Tension	26.0
Compression	26.0
Torsion	9.5
Poisson's Ratio	0.32
Curie Temperature, °F	70-120
°C	21-49

^aThese values also apply to MONEL alloy R-405, the free-machining version of MONEL alloy 400.

MONEL® alloy 400

Publication Number SMC-053

Copyright © Special Metals Corporation, 2005 (Feb 05)

MONEL, INCONEL, and INCOFLUX are trademarks of the Special Metals Corporation group of companies.

The data contained in this publication is for informational purposes only and may be revised at any time without prior notice. The data is believed to be accurate and reliable, but Special Metals makes no representation or warranty of any kind (express or implied) and assumes no liability with respect to the accuracy or completeness of the information contained herein. Although the data is believed to be representative of the product, the actual characteristics or performance of the product may vary from what is shown in this publication. Nothing contained in this publication should be construed as guaranteeing the product for a particular use or application.



MONEL® alloy 400

Table 3 - Thermal Properties of MONEL Alloy 400

Temperature		Mean Linear Expansion ^b		Thermal Conductivity ^a		Specific Heat ^a		Electrical Resistivity ^{a,c}	
°F	°C	in/in/°F x 10 ⁻⁶	µm/m·°C	Btu-in/h/ft ² /°F	W/m·°C	Btu/lb/°F	J/kg·°C	ohm-circ mil/ft	µΩ·m
-320	-200	-	-	-	-	-	-	205	.360
-300	-180	6.1	11.1	113	16.5	0.050	223	-	-
-200	-130	6.4	11.4	130	18.2	0.078	320	-	-
-100	-70	6.7	12.1	139	19.8	0.088	378	-	-
70	21	-	-	151	22.0	0.102	427	307	0.511
200	100	7.7	14.2	167	24.0	0.105	445	322	0.537
400	200	8.6	15.2	193	26.9	0.110	459	337	0.559
600	300	8.8	15.7	215	30.1	0.114	470	346	0.574
800	400	8.9	16.1	238	33.4	-	-	355	0.587
1000	500	9.1	16.3	264	36.5	-	-	367	0.603
1200	600	9.3	16.6	287	39.4	-	-	379	0.620
1400	700	9.6	17.0	311	42.4	-	-	391	0.639
1600	800	9.8	17.4	335 ^d	45.5 ^d	-	-	403	0.658
1800	900	10.0 ^d	17.7	360 ^d	48.8 ^d	-	-	415	0.675
2000	1000	10.3 ^d	18.1 ^d	-	-	-	-	427	0.692

^aThese values also apply to MONEL alloy R-405, the free-machining version of MONEL alloy 400.

^bAnnealed material. Between 70°F (21°C) and temperature shown.

^cAnnealed material.

^dExtrapolated.




Figure 1. Effect of temperature on modulus of elasticity in tension of MONEL alloy 400 (determined by dynamic method).

MECHANICAL PROPERTIES

Tensile Properties and Hardness

The nominal room-temperature tensile properties of MONEL alloy 400 are shown in Table 4. Additional data on hardness of various tempers of sheet and strip are in Table 5.

Figures 2 and 3 are based on typical data that show relationships between properties of rods and forgings and sheet and strip.

Short-time high-temperature properties of hot-rolled annealed material are shown in Figure 4.

MONEL alloy 400 has excellent mechanical properties at subzero temperatures. Strength and hardness increase with only slight impairment of ductility or impact resistance. The alloy does not undergo a ductile-to-brittle transition even when cooled to the temperature of liquid hydrogen. This is in marked contrast to many ferrous materials which are brittle at low temperatures despite their increased strength. Table 6 shows mechanical properties of the alloy at low temperatures.

Table 4 - Nominal Room-Temperature Tensile Properties of MONEL Alloy 400^a

Form and Condition	Tensile Strength		Yield Strength (0.2% Offset)		Elongation, %	Hardness	
	ksi	MPa	ksi	MPa		Brinell (3000-kg)	Rockwell B
Rod and Bar							
Annealed	75-90	517-620	25-50	172-345	60-35	110-149	60-80
Hot-Finished (except Hexagons over 2 1/8 inches and Angles)	80-110	552-758	40-100	276-690	60-30	140-241	75-100
Hot-Finished Hexagons over 2 1/8 inches and Angles	75-100	517-690	30-55	207-379	50-30	130-184	72-90
Cold-Drawn, Stress-Relieved	84-120	579-827	55-100	379-690	40-22	160-225	85-20C
Plate							
Hot-Rolled, As-Rolled	75-95	517-655	40-75	276-517	45-30	125-215	70-96
Hot-Rolled, Annealed	70-85	482-586	28-50	193-345	50-35	110-140	60-76
Sheet							
Annealed	70-85	482-586	30-45	207-310	45-35	-	65-80
Cold-Rolled, Hard	100-120	690-827	90-110	621-758	15-2	-	93 min. ^a
Strip, Cold-Rolled							
Annealed	70-85	482-586	25-45	172-310	55-35	-	68 max. ^a
Spring Temper	100-140	690-965	90-130	621-896	15-2	-	98 min. ^a
Tube and Pipe, Seamless							
Cold-Drawn, Annealed	70-85	482-586	25-45	172-310	50-35	-	75 max. ^a
Cold-Drawn, Stress-Relieved	85-120	586-827	55-100	379-690	35-15	-	85-100 ^a
Heat-Exchanger, Annealed	70-85	482-586	28-45	193-310	50-35	-	75 max. ^a
Heat-Exchanger, Stress-Relieved	85-105	586-724	55-90	379-621	35-15	-	85-97 ^a
Hot-Extruded	_b	_b	_b	_b	_b	-	_b
No. 1 Temper (Annealed)	85 max.	586 max.	30-45	207-310	45-30	-	73 max. ^a
No. 2 Temper (Half-Hard)	85-105	586-724	55-80	379-552	30-10	-	75-97 ^a
No. 3 Temper (Full-Hard)	110-130	758-896	90-110	621-758	10-3	-	95-27C
Wire, Cold Drawn ^c							
Annealed	70-95	482-655	30-55	207-379	45-25	-	-
No. 1 Temper	85-100	586-690	50-75	345-517	30-20	-	-
Quarter-Hard	95-120	655-827	65-95	448-655	25-15	-	-
Half-Hard	110-135	758-931	85-120	586-827	15-8	-	-
Three-Quarter-Hard	125-150	862-1034	100-135	690-931	8-5	-	-
Full-Hard--Spring Temper	145-180	1000-1241	125-170	862-1172	5-2	-	-

^aThe ranges shown are composites for various product sizes and therefore are not suitable for specification purposes. Hardness values are suitable for specification purposes providing tensile properties are not also specified.

^bProperties on request.

^cProperties shown are for sizes from 0.032 to 0.250-in. diameter. Properties for other sizes may vary from these.

Torsional Strength

Some torsional properties of alloy 400 are shown in Table 7.

Compressive Strength

Compressive properties, determined in triplicate on single typical melts, are shown in Table 8 along with the corresponding tensile properties and hardness. The modulus of elasticity in compression is the same as that in tension. More detailed information may be found elsewhere.

Table 5 - Hardness of Cold-Rolled MONEL Alloy 400 Sheet and Strip

Temper	Rockwell B Hardness	
	Sheet	Strip
Deep-Drawing and Spinning Quality	76 max.	76 max.
Annealed ^a	73 max.	68 max.
Skin-Hard	-	68-73
Quarter-Hard	73-83	73-83
Half-Hard	82-90	82-90
Three-Quarter-Hard	-	89-94
Hard	93 min.	93-98
Spring	-	98 min.

^aHardness for information only where tensile requirements apply.

MONEL® alloy 400




Figure 2. Approximate relationships between tensile properties and hardness of hot-rolled and cold-drawn MONEL alloy 400 rods and forgings.




Figure 3. Approximate relationships between tensile properties and hardness of MONEL alloy 400 sheet and strip.

Table 6 - Tensile Properties of MONEL Alloy 400 at Low Temperatures

Temper	Temperature, °F	Tensile Strength, ksi	Yield Strength (0.2% Offset), ksi	Elongation, %	Reduction of Area, %
Cold-Drawn	Room	103.80	93.70	19.0	71.0
	-110	117.45	100.85	21.8	70.2
Forged	Room ^a	103.40	93.30	17.3	72.5
	70	92.00	67.00	31.0	72.7
	-297	128.25	91.50	44.5	71.8
Annealed	-423	142.00	96.40	38.5	61.0
	70	78.65	31.30	51.5	75.0
	-297	115.25	49.50	49.5	73.9

^aHeld at -110°F for several hours prior to testing at room temperature.




Figure 4. High-temperature properties of annealed MONEL alloy 400.

Shear Strength

Room-temperature shear strength of MONEL alloy 400 sheet is shown in Table 9. The values are the averages of several tests. The shear strength of rivet wire at various temperatures is given in Table 10. Shear properties were determined on 1/8-in. diameter wire in double shear.

In U.S. Navy tear tests at temperatures down to -320°F, the material showed excellent ductility and tough fracture characteristics over this temperature range with the maximum load increasing considerably with decrease in temperature. The data appear in Table 11.

Bearing Strength

It is possible, in riveted joints, for failure to occur by tearing out a segment of sheet instead of by shearing the rivet. The resistance of sheet metal to this deformation is known as bearing strength. It can be evaluated by using a hard pin or rivet to enlarge or tear a hole in a sample of sheet metal.

The data shown in Table 12 were determined with samples 0.062 X 1.25 X 2.5 in. in size having a 3/16-in. hole located so that its center was 3/8-in. from the edge. A snugly fitted pin was placed in the hole. The maximum load for tearing out the hole and the load required for a permanent enlargement of the hole diameter by 2% were determined and calculated as ultimate and yield strengths, respectively, in bearing.

Table 7 - Torsional Properties of MONEL Alloy 400

Form and Condition	Dia., in.	Tensile Properties		Torsional Properties		Ratio		
		Tensile Strength, ksi	Yield Strength (0.2% Offset), ksi	Breaking Strength, ksi	Proportional Limit, ksi	Breaking Strength Torsional/Tensile Strength	Torsional Proportional Limit/Tensile Strength	Torsional Proportional Limit/Torsional Breaking Strength
Wire								
Cold-Drawn, 75%	0.148	157	-	110	68	0.700	0.433	0.618
Cold-Drawn, 75% Stress-Relieved	0.148	160	-	105	65	0.656	0.404	0.619
Rod								
Hot-Rolled	1	86	38	66	23	0.768	0.267	0.349
Cold-Drawn, 20%	1	115	107	72	47	0.626	0.408	0.653
	1.5	113	102	71	45	0.628	0.398	0.634

MONEL[®] alloy 400

Table 8 - Compressive Properties of MONEL Alloy 400

Temper	Compression		Tension			
	Yield Strength (0.01% Offset), ksi	Yield Strength (0.2% Offset), ksi	Tensile Strength, ksi	Yield Strength (0.01% Offset), ksi	Yield Strength (0.2% Offset), ksi	Elongation, %
Hot-Rolled	33	38	84	37	41	39.5
Cold-Drawn ^a	58	81	97	75	87	27.0
Annealed ^b	19	28	78	28	33	44.0

^aStress-equalized at 525°F after cold drawing.

^bCold-drawn +1450°F/3 hr, F.C.

Table 9 - Shear Strength of MONEL Alloy 400 Sheet^a

Temper	Thickness, in.	Shear Strength, ksi	Tensile Strength, ksi	Hardness, Rb	Ratio Shear Strength/ Tensile Strength
Hot-Rolled, Annealed	0.042	48.75	73.0	65	0.67
Cold-Rolled, Annealed	0.029	49.50	76.8	60	0.65

^aDouble-shear tests at room temperature.

Table 10 - Shear Strength of MONEL Alloy 400 Rivet Wire

Property	Condition	
	Annealed	B & S No. 1 ^a
Shear Strength, ksi		
Room	48.5	54.5
600 ^b	45.0	52.0
800 ^b	37.0	47.5
1000 ^b	29.0	38.0
800 ^c	38.5	49.5
1000 ^c	30.5	38.5
Tensile Strength, ksi	78.5	88.0
Yield Strength (0.2% Offset), ksi	46.0	75.5
Elongation, %	41	18

^aCorresponds to the approximate strength of the shank of a headed rivet.

^b30 min at temperature before testing.

^c24 hr at temperature before testing.

Table 11 - U. S. Navy Tear Tests on MONEL Alloy 400 Hot-Rolled Plate^a

Temperature, °F	Maximum Load, lb	Corrected Energy Values, ft-lb			Reduction of Thickness, %
		Initiation	Propagation	Total	
Room	32,340	715	2008	2723	57.0
-184	39,000	649	2402	3051	50.0
-238	42,000	795	2408	3203	51.0
-320	47,800	899	2802	3701	46.0
-320 ^b	41,300	676	2138	2814	45.0

^aIn all cases, appearance of fracture was double-cup shear.

^bTested with jeweler's-saw notch

Table 12 - Bearing Strength of MONEL Alloy 400 Sheet

Temper	Tensile Properties			Bearing Strength		Ratio, Bearing Strength/	
	Tensile Strength, ksi	Yield Strength (0.2% Offset), ksi	Elongation, %	Yield Strength ^a , ksi	Ultimate Strength ^b , ksi	Yield Strength	Ultimate Strength
Annealed	70.0	27.2	42.5	58.0	145.0	2.13	2.07
Half-Hard	75.8	56.2	32.0	98.1	166.0	1.75	2.19
Full-Hard	117.8	110.0	5.0	162.0	211.5	1.47	1.79

^a2% enlargement of hole diameter in sheet.

^bTearing out of sheet.

Impact Strength

MONEL alloy 400 is notable for its toughness, which is maintained over a considerable range of temperatures. Table 13 shows room-temperature Charpy and Izod impact strength values as determined on typical material from production melts. Tension and torsion impact data appear in Tables 14 and 15. Complete fractures occurred in the tension impact test specimens whereas the torsion specimens remained intact. Attempts to produce fractures in the torsion specimens by reducing the minimum area by 75% were not successful because of the toughness of the material.

Table 13 - Impact Strength of MONEL Alloy 400^a

Temper	Impact Strength, ft•lb	
	Izod	Charpy U Notch
Hot-Rolled	100-120+	220
Forged	75-115	-
Cold-Drawn	75-115	150
Annealed	90-120+	215

^aTested at room temperature. None of the specimens was completely fractured.

Table 14 - Tension Impact Strength of MONEL Alloy 400 Rod

Temper	Tensile Impact			Tensile Properties				
	Impact Strength, ft•lb	Elongation in 3.54 in., %	Reduction of Area, %	Tensile Strength, ksi	Yield Strength (0.2% Offset), ksi	Elongation in 2 in., %	Reduction of Area, %	Hardness, Brinell (3000-kg)
Cold Drawn 24% Stress Relieved	96 ^a	15.0	63.7	97.25	86.65	27.0	66.4	199
Annealed 1450°F/3 hr	129 ^a	29.5	68.0	78.35	33.35	44.0	65.9	123

^aSpecimen completely broken.

Table 15 - Charpy Torsion Impact Strength of MONEL Alloy 400 Rod

Temper	Impact Strength		Angle of Twist ^a , Degree	Hardness, Brinell (3000-kg)
	ft•lb	ft•lb/in ²		
Hot-Rolled	34	694	101.5	145
Cold-Drawn 24%, Stress-Relieved	39	788	98.0	199
Annealed 1450°F/3 hr	30	599	102.0	123

^aGage length about 3/16 in.

The effect of decrease of temperature on impact strength appears in Table 16. Impact tests conducted on hot-finished plate at liquid-hydrogen and liquid-helium temperatures are summarized in Table 17. Tests were conducted on samples representing both longitudinal and transverse orientation in the plate, and on welded samples. No evidence of brittle fractures was shown. The welded specimens all fractured in the weld. No significant amount of anisotropy was evidenced.

Table 16 - Impact Strength of MONEL Alloy 400 (Charpy V-Notch)

Temper	Impact Strength, ft•lb			
	75°F	-20°F	-112°F	-310°F
Hot-Rolled	219	-	213	196
Cold-Drawn, Annealed	216	212	219	212
Weld, As-Welded	78	-	-	73

MONEL® alloy 400

Table 17 - Charpy Impact Strength of Hot-Finished MONEL Alloy 400 Plate

Temperature, °F	Notch	Orientation	Impact Strength, ft•lb
-423 ^a	V	Long.	141-219
-423 ^a	V	Trans.	121-216
-423 ^a	Keyhole	Long.	81-87
-423 ^a	Keyhole	Trans.	72-75
-440 ^b	V	Long.	Unbroken
-440 ^b	V	Trans.	171-193
-440 ^b	Keyhole	Long.	123-146
-440 ^b	Keyhole	Trans.	91-116

^aRange for 5 tests liquid-hydrogen temperature.

^bRange for 4 tests at liquid-helium temperature.

Fatigue Strength

Fatigue strength of various tempers of alloy 400 is given in Table 18. Values for sheet and strip are in Table 19, cold drawn wire in Figure 5, and annealed rod in Figure 6.

Table 18 - Fatigue Strength^a of MONEL Alloy 400 Rod

Temper	Fatigue Strength (10 ⁸ cycles), ksi	Tensile Strength, ksi	Ratio, Fatigue Strength/Tensile Strength
Annealed	33.5	82.0	0.41
Hot-Rolled	42.0	88.0	0.48
Cold-Drawn, As-Drawn	40.5	105.0	0.39
Cold-Drawn, Stress-Equalized ^b	44.0	104.0	0.42
Cold-Drawn, Stress-Relieved ^c	37.0	96.5	0.38

^aRotating-beam tests of polished specimens in air at room temperature and 10,000 rpm.

^b525°F/3 hr.

^c1000°F/3 hr.

Table 19 - Fatigue Strength of MONEL Alloy 400 Sheet and Strip^a

Temper	Fatigue Strength (10 ⁸ cycles), ksi	Tensile Strength, ksi	Ratio, Fatigue Strength/Tensile Strength
Annealed	21.0	74.7	0.28
Quarter-Hard	24.5	76.5	0.32
Half-Hard	28.5	84.2	0.34
Full-Hard	39.0	126.0	0.31
Full-Hard, Stress-Equalized (525°F/21 hr)	41.0	133.0	0.31

^aAs-rolled surface. Tested in air at room temperature. Specimen length parallel to direction of rolling. Completely reversed stress.




Figure 5. Fatigue strength of commercially produced MONEL alloy 400 wire (0.0375-in. diameter, cold-drawn 75% after final anneal). Tested in processed condition. Data determined with a rotating-wire (5000 rpm) arc-fatigue machine.




Figure 6. Fatigue strength of commercially produced MONEL alloy 400 rod (0.500-in. diameter, cold-drawn, annealed 1500°F/3 hrs). Tested in the processed condition. Data determined by the R.R. Moore rotating beam technique.

Creep and Rupture Properties

MONEL nickel-copper alloy 400 is useful at temperatures up to and including 1000°F in oxidizing atmospheres. Higher temperatures may be employed if the alloy is in a reducing environment.

Creep and rupture properties are shown in Figures 7-11.




Figure 7. Creep properties of hot-rolled MONEL alloy 400.




Figure 8. Creep properties of cold-drawn annealed (1500°F/3 hr) MONEL alloy 400.




Figure 9. Creep properties of 20% cold-drawn stress-relieved (1000°F/8 hr) MONEL alloy 400.

MONEL® alloy 400




Figure 10. Rupture properties of cold-drawn annealed (1500°F/30 min) MONEL alloy 400.




Figure 11. Rupture properties of cold-drawn, stress-relieved (1100°F/8 hr) MONEL alloy 400.

MICROSTRUCTURE

MONEL alloy 400 is a solid-solution binary alloy. As nickel and copper are mutually soluble in all proportions, it is a single-phase alloy. It has a face-centered cubic lattice structure with a lattice parameter of 3.534 Å. Figure 12 shows the typical microstructure of the material.

In the unetched condition, a polished specimen of MONEL alloy 400 will exhibit only randomly dispersed nonmetallic inclusions. These consist of metal sulfides or silicates. Under some conditions, graphite particles may also be present.




Figure 12. Longitudinal section of cold-drawn MONEL alloy 400 rod. Etchant: Sodium cyanide--ammonium persulfate. 100X.

CORROSION RESISTANCE

MONEL alloy 400 exhibits resistance to corrosion by many reducing media. It is also generally more resistant to attack by oxidizing media than higher copper alloys. This versatility makes alloy 400 suitable for service in a variety of environments.

Alloy 400 is widely used in marine applications. While alloy 400 products exhibit very low corrosion rates in flowing seawater, stagnant conditions have been shown to induce crevice and pitting corrosion. Alloy 400 is also resistant to stress corrosion cracking and pitting in most fresh and industrial waters.

MONEL alloy 400 offers exceptional resistance to hydrofluoric acid in all concentrations up to the boiling point. It is perhaps the most resistant of all commonly used engineering alloys. Alloy 400 is also resistant to many forms of sulfuric and hydrochloric acids under reducing conditions.

For information on the resistance of alloy 400 and other alloys to attack by various corrosive media, the reader is directed to the Special Metals publication "High Performance Alloys for Resistance to Aqueous Corrosion" on the website www.specialmetals.com.

WORKING INSTRUCTIONS

MONEL alloy 400 can be readily joined and fabricated. By proper control of the amount of hot or cold work and by the selection of appropriate thermal treatments, finished fabrications can be produced to a rather wide range of mechanical properties.

Heating and Pickling

THERMAL TREATMENTS. General procedures and precautions for heating alloy 400 either in preparation for hot working or for achievement of desired mechanical properties may be found in the Special Metals publication "Fabricating," on the website www.specialmetals.com. The material will remain bright and free from discoloration when heated and cooled in a reducing atmosphere or quenched in an alcohol-water solution. Rate of cooling will have no significant effect. Alloy 400 will form an adherent oxide film if allowed to cool in air after heating.

Both cold-worked and hot-worked MONEL alloy 400 requires thermal treatment to develop the optimum combination of strength and ductility and to minimize distortion during subsequent machining. How thermal treatment affects properties is shown in Figure 13.

Stress equalizing of cold-worked material causes an increase in the yield strength at 0.00% offset without marked effects on other properties (see Figure 13). Stress equalizing is done by holding for about 3 hr at a temperature of 575°F.

Stress relieving will reduce stresses without producing a recrystallized grain structure. This treatment is recommended to obtain minimum "walking" or distortion after metal removal. Heating for 1 to 2 hr at 1000° to 1050°F will relieve strains in either hot or cold-worked products. Stress relief (1000°-1200°F/1 hr, followed by slow cooling) is strongly recommended as a precaution against stress-corrosion cracking in certain environments. As shown in Figure 13, stress relieving slightly decreases tensile strength, yield strength, and hardness and slightly increases elongation.

Annealing can completely soften work-hardened material. Time and temperature required depend on the amount of previous cold work. In general, alloy 400 is annealed by the open heating method by holding at 1600° to 1800°F for 2-10 min, whereas box annealing is done most

satisfactory at 1400° to 1500°F for 1-3 hr at temperature.

The effects of heating on properties of cold-drawn and hot-rolled material are compared in Figures 13 and 14. In these tests, the cold-drawn rod developed an annealed temper after 3 hr at temperature at 1300°F, and the hot-rolled plate, after 3 hr at about 1470°F. More data on time-temperature-hardness relationships are shown in Figure 15. They may be used as guides for establishing procedures for specific applications.

Grain growth occurs when material is heated in the upper portion of the annealing temperature range. Figure 16 indicates grain sizes which may be expected from open annealing of cold-rolled strip.

PICKLING. Pickling can produce bright, clean surfaces on MONEL alloy 400. Procedures and precautions are described in the Special Metals publication, "Fabricating," on the website www.specialmetals.com.

Fabricating

MONEL alloy 400 is readily fabricated by standard processes. Special recommendations may be found in the Special Metals publication "Fabricating," at www.specialmetals.com.

Hot Forming. With respect to its resistance to hot deformation, MONEL alloy 400 is softer than many steels. It can, therefore, be hot-formed into almost any shape.

The use of proper temperature during hot forming is important. The range of hot-forming temperatures is 1200°F to 2150°F. For heavy reductions, recommended metal temperature is 1700° to 2150°F. Light reductions may be taken down to 1200°F. Working at the lower temperatures produces higher mechanical properties and smaller grain size.

Prolonged soaking at hot-working temperatures is detrimental. If a delay occurs during processing, the furnace should be cut back to 1900°F and not brought to temperature until operations are resumed. In no case should the alloy be heated above 2150°F; permanent damage may result.

Heavy forging should not be carried out so rapidly that the metal becomes overheated from working. The use of an optical pyrometer is recommended.

MONEL® alloy 400




Figure 13. Effect of annealing (3 hr) on room-temperature properties of MONEL alloy 400 cold-drawn rod.




Figure 14. Effect of annealing (3 hr) on room-temperature properties of hot-rolled MONEL alloy 400 plate. At 1470°F, material is fully annealed. (Hardness converted from BHN.).




Figure 15. Approximate time required at various temperatures to produce different hardness levels in MONEL alloy 400 cold-rolled strip by open annealing.




Figure 16. Approximate time required at various temperatures to produce different grain sizes in MONEL alloy 400 cold-rolled strip by open annealing.

In hot-bending operations the metal should be worked as soon as possible after removal from the furnace.

Preheating tools and dies to about 500°F is helpful to prevent chilling the material while working.

A controlled forging procedure is necessary to meet the requirements of some specifications for forged, hot-finished parts. Both the amount of reduction and the finishing temperature must be controlled in order to develop the desired properties.

One procedure for producing forgings to such specifications consists of taking 30-35% reduction following the final reheat.

This is accomplished as follows:

1. Reheat.
2. Forge to a section having about 5% larger area than the final shape (take at least 25% reduction).
3. Cool to 1300°F.
4. Finish to size (5% reduction).

High-tensile forgings, as described in certain military specifications, also require a minimum of 30-35% reduction following the last reheat. This is taken in the following manner:

1. Reheat.
2. Forge to a section having an area about 25% larger than the final shape (take about 5% reduction).
3. Cool to 1300°F.
4. Finish to size (25% reduction).

Grain refinement is achieved by using a temperature of 2000°F for the final reheat and by increasing the amount of reduction taken after the last reheat.

Cold Forming. MONEL alloy 400 is adaptable to virtually

all methods of cold fabrication. The forces required and the rate of work hardening are intermediate between those of mild steel and Type 304 stainless steel (see Figure 17).




Figure 17. Effect of cold work on hardness.

Machining

Alloy 400 can be machined at satisfactory rates with machine tools generally employed by industry. The best tool materials and design, speeds, coolants, and other factors are discussed in the Special Metals publication “Machining.” In general, cold-drawn or cold-drawn, stress-relieved material is recommended for best machinability and smoothest finish. MONEL alloy R-405 is the free-machining version of MONEL alloy 400. Additional information on machining is available in the Special Metals publication “Machining” on the website, www.specialmetals.com.

Joining

MONEL alloy 400 is readily joined by conventional processes and procedures. Information on welding, brazing, and soldering are found in the Special Metals publication “Joining”, on the website www.specialmetals.com.

Most of the conventional welding processes may be used to join MONEL alloy 400 to itself or dissimilar alloys. The choice of welding product is dependent upon the materials being joined and the environment to which they will be exposed.

For shielded metal arc welding (SMAW), MONEL Welding Electrode 190 is used to deposit near-matching composition weldments. For some applications, Nickel Welding Electrode 141, INCO-WELD A Welding Electrode, or INCONEL Welding Electrode 112 may be preferred. Properties of weldments deposited with MONEL Welding Electrode 190 between two sections of MONEL alloy 400 plate and between sections of alloy 400 and carbon steel plate are shown in Tables 20 and 21.

For gas tungsten arc welding (GTAW) and gas metal arc welding (GMAW), MONEL Filler Metal 60 is used to deposit near-matching composition weldments. For some applications, Nickel Filler Metal 61 or INCONEL Filler Metal 625 may be preferred. These same filler metals may be used for submerged arc welding (SAW). INCOFLUX 5 is used with MONEL Filler Metal 60. INCOFLUX 6 is used with Nickel Filler Metal 61. INCONEL Filler Metal 625 is used with INCOFLUX 7.

Additional information on joining is available in the Special Metals publication “Joining” on the website, www.specialmetals.com.

MONEL® alloy 400

Table 20 - High-Temperature Tensile Properties of MONEL Alloy 400 Welds Made with MONEL Welding Electrode 190^a

Temperature, °F	Tensile Strength, ksi	Yield Strength (0.2% Offset), ksi	Elongation, %	Reduction of Area, %
		All-Weld Metal		
Room	74.35	46.65	41.0	66.4
200	42.25	46.05	39.0	56.5
400	68.60	43.10	33.5	64.2
600	69.25	43.15	34.0	59.9
800	66.10	43.00	32.5	47.4
1000	55.95	38.70	22.0	24.5
		Transverse Across Weld ^b		
Room	76.2	48.50	24.0	48.0
400	69.6	45.00	24.0	58.3
600	68.5	45.80	21.0	56.5
800	69.0	41.00	28.0	44.2

^aButt joints--1/2-in. MONEL alloy 400.

^bAll breaks occurred in weld.

Table 21 - Room-Temperature Properties of Butt Joint Weld of 1 1/4-in. MONEL Alloy 400 and Steel Using MONEL Welding Electrode 190

Property	As-Welded		Heat-Treated 1150°F/10 hr, A.C.	
	All-Weld Metal	Transverse Across Weld ^a	All-Weld Metal	Transverse Across Weld ^a
Tensile Strength, ksi	71.0	78.0	70.5	76.4
Yield Strength, ksi	48.3	51.5	45.3	36.7
Elongation, %	38	21	38	31
Reduction of Area, %	63.3	60.5	63.3	59.3

^aBreak occurred in weld.

AVAILABLE PRODUCTS AND SPECIFICATIONS

MONEL alloy 400 is designated as UNS N04400 and Werkstoff Nr. 2.4360 and 2.4361. It is listed in NACE MR-01-75 for oil and gas service. Alloy 400 is furnished in a wide range of standard mill forms including pipe, tube, sheet, strip, plate, round bar, flat bar, forging stock, hexagon and wire. Popular forms and sizes are available from stock; many specialty products may be obtained from converters.

MONEL alloy 400 is approved as a material of construction by the ASME Boiler and Pressure Vessel Code. Allowable stresses for Section III construction up to 800°F, Section VIII Division 1 construction up to 900°F and Section VIII Division 2 construction up to 800°F are contained in Tables 1B and 2B of ASME Section II, Part D.

Plate, Sheet, and Strip - BS3072NA13 (Sheet and Plate), BS3073NA13 (Strip), ASTM B 127, ASME SB 127 (Plate, Sheet, and Strip), SAE AMS 4544 (Sheet, Strip, and Plate), DIN 17750 (Plate, Strip and Sheet), QQ-N-281 (Plate, Sheet, Strip, Bar, Rod, Wire, and Forgings)

Bar, Rod, Wire, and Forgings - BS3075NA13 (Wire), BS3076NA13 (Bar), ASTM B 164 (Rod, Bar, and Wire), ASTM B 564 (Forgings), ASME SB 164 (Rod, Bar, and Wire), ASME SB 564 (Forgings), AECMA PrEN 2305 (Wire for Rivets), SAE AMS 4675 (Bars and Forgings),

SAE AMS 4730 (Wire), SAE AMS 4731 (Wire and Ribbon), DIN 17752 (Rod and Bar), DIN 17753 (Wire), DIN 17754 (Forgings), VdTÜV 263 (Sheet, Plate, Bar, and Tubing), QQ-N-281 (Plate, Sheet, Strip, Bar, Rod, Wire, and Forgings)

Pipe and Tube - BS3074NA13 (Tube), ASTM B 163 (Condenser and Heat Exchanger Tube), ASTM B 165 (Seamless Pipe and Tube), ASTM B 725 (Welded Pipe), ASTM B 730 (Welded Tube), ASTM B 751 (Welded Tube), ASTM B 775 (Welded Pipe), ASTM B 829 (Seamless Pipe and Tube), ASME SB 163 (Condenser and Heat Exchanger Tubes), ASME SB 165 (Seamless Pipe and Tube), ASME SB 725 (Welded Pipe), ASME SB 730 (Welded Tube), ASME SB 751 (Seamless and Welded Tube), ASME SB 775 (Seamless and Welded Pipe), ASME SB 829 (Seamless Pipe and Tube), SAE AMS 4574 (Seamless Tubing), DIN 17751 (Pipe and Tube), VdTÜV 263 (Sheet, Plate, Bar, and Tubing),

Welding Products - MONEL Filler Metal 60-AWS A5.14/ERNiCu-7; MONEL Welding Electrode 190-AWS A5.11/ENiCu-7.

Other Products - ASTM B 366, ASME SB 366 (Welded Fittings), SAE AMS 7233 (Rivets), DIN 17743 (Chemical Composition)

The Special Metals Corporation
trademarks include: _____

BRIGHTRAY[®]
CORRONEL[®]
DEPOLARIZED[®]
DURANICKEL[®]
FERRY[®]
INCOBAR[®]
INCOCLAD[®]
INCO-CORED[®]
INCOFLUX[®]
INCOLOY[®]
INCONEL[®]
INCOTEST[®]
INCOTHERM[®]
INCO-WELD[®]
KOTHERM[®]
MONEL[®]

NILO[®]
NILOMAG[®]
NIMONIC[®]
NIOTHERM[®]
NI-ROD[®]
NI-SPAN-C[®]
RESISTOHM[®]
UDIMAR[®]
UDIMET[®]
601GC[®]
625LCF[®]
718SPF[™]
725NDUR[®]
800HT[®]
956HT[™]





www.specialmetals.com

**U.S.A.
Special Metals Corporation**

Billet, rod & bar, flat & tubular products
3200 Riverside Drive
Huntington, WV 25705-1771
Phone +1 (304) 526-5100
+1 (800) 334-4626
Fax +1 (304) 526-5643

Billet & bar products
4317 Middle Settlement Road
New Hartford, NY 13413-5392
Phone +1 (315) 798-2900
+1 (800) 334-8351
Fax +1 (315) 798-2016

Atomized powder products
100 Industry Lane
Princeton, KY 42445
Phone +1 (270) 365-9551
Fax +1 (270) 365-5910

Shape Memory Alloys
4317 Middle Settlement Road
New Hartford, NY 13413-5392
Phone +1 (315) 798-2939
Fax +1 (315) 798-6860

France

Special Metals Services SA
17 Rue des Frères Lumière
69680 Chassieu (Lyon)
Phone +33 (0) 4 72 47 46 46
Fax +33 (0) 4 72 47 46 59

Germany

Special Metals Deutschland Ltd.
Postfach 20 04 09
40102 Düsseldorf
Phone +49 (0) 211 38 63 40
Fax +49 (0) 211 37 98 64

Hong Kong

Special Metals Pacific Pte. Ltd.
Unit A, 17th Floor, On Hing Bldg
1 On Hing Terrace
Central, Hong Kong
Phone +852 2439 9336
Fax +852 2530 4511

India

Special Metals Services Ltd.
No. 60, First Main Road, First

Affiliated Companies

Special Metals Welding Products
1401 Burriss Road
Newton, NC 28658, U.S.A.
Phone +1 (828) 465-0352
+1 (800) 624-3411
Fax +1 (828) 464-8993

Canada House
Bidavon Industrial Estate
Waterloo Road
Bidford-On-Avon
Warwickshire B50 4JN, U.K.
Phone +44 (0) 1789 491780
Fax +44 (0) 1789 491781

Controlled Products Group
590 Seaman Street, Stoney Creek
Ontario L8E 4H1, Canada
Phone +1 (905) 643-6555
Fax +1 (905) 643-6614

A-1 Wire Tech, Inc.
A Special Metals Company
4550 Kishwaukee Street
Rockford, IL 61109, U.S.A.
Phone +1 (815) 726-0477

CABLE JOINTS, CABLE TERMINATIONS, CABLE GLANDS, CABLE CLEATS
FEEDER PILLARS, FUSE LINKS, ARC FLASH, CABLE ROLLERS, CUT-OUTS

11KV 33KV CABLE JOINTS & CABLE TERMINATIONS
FURSE EARTHING
www.cablejoints.co.uk
Thorne and Derrick UK

Tel 0044 191 490 1547 Fax 0044 191 477 5371
Tel 0044 117 977 4647 Fax 0044 117 9775582

Special Metals Services SpA
Via Assunta 59
20054 Nova Milanese (MI)
Phone +390 362 4941
Fax +390 362 494224

The Netherlands

Special Metals Service BV
Postbus 8681
3009 AR Rotterdam
Phone +31 (0) 10 451 44 55
Fax +31 (0) 10 450 05 39

Singapore

Special Metals Pacific Pte. Ltd.
24 Raffles Place
#27-04 Clifford Centre
Singapore 048621
Phone +65 6532 3823
Fax +65 6532 3621

China

Special Metals Pacific Pte. Ltd.
Room 1802, Plaza 66
1266 West Nanjing Road
Shanghai 200040
Phone +86 21 3229 0011
Fax +86 21 6288 1811

Special Metals Pacific Pte. Ltd.
Room 910, Ke Lun Mansion
12A Guanghua Road
Chaoyang District
Beijing 100020
Phone +86 10 6581 8396
Fax +86 10 6581 8381

