

2228 Rubber Mastic Tape

Data Sheet

Product Description

Scotch 2228 is a conformable self-fusing rubber electrical insulating and sealing tape. Scotch 2228 consists of an ethylene propylene rubber (EPR) backing coated with an aggressive, temperature-stable mastic adhesive. The tape is 1.65mm thick for quick application build-up. It is designed for electrical insulating and moisture sealing applications. Scotch 2228 can be used on copper or aluminium conductors rated at 90°C, with an emergency overload rating of 130°C. It offers excellent resistance to moisture and ultraviolet exposure and is intended for both indoor and weather exposed outdoor applications.

Tape Features:

- ❖ Conformable for application over irregular surfaces
- ❖ Compatible with solid dielectric cable insulations
- ❖ Self-fusing tape
- ❖ Flexible over wide temperature range
- ❖ Excellent weather and moisture resistance
- ❖ Excellent adhesion and sealing characteristics with copper, aluminium and power cable jacket materials
- ❖ Thick construction allows quick application build-up and padding over irregular connections

Applications

- ❖ Primary electrical insulation for cable and wire connections rated up to 1000 volts
- ❖ Electrical insulation and vibration padding for motor leads rated up to 1000 volts
- ❖ Primary electrical insulation for bus bar connections rated up to 35kV (3M drawing 2047B-106)
- ❖ Padding for irregular shaped bus bar bolted connections
- ❖ Moisture seal for cable and wire connections
- ❖ Moisture seal for service drops
- ❖ Moisture seal for ground wire and rod connections
- ❖ Jacket seal on power cable applications

Typical Data/Physical Properties

Temperature Rating

ASTM D-4388 194°F (90°C)

Colour

Black

Thickness

ASTM D-4325 1.65mm

Adhesion

ASTM D-1000

Steel 26.2N/10mm
PE 17.5N/10mm

Fusion

ASTM D-4388, Type 1 Pass

Tensile Strength

ASTM D-4325 1.03N/mm²

Elongation

ASTM D-4325 100%

Dielectric Breakdown

ASTM D-4325

Dry 19.7kV/mm
Wet 19.7kV/mm

Dielectric Constant

ASTM D-4325 3.5

Dissipation Factor

ASTM D-4325 1.0%

Water Absorption

ASTM-570 0.15%

Water Vapour Transmission Rate

ASTM D-3833 0.1g/100in²/24hr

Ozone Resistance

ASTM D-3833 Pass

Heat Resistance

ASTM D-4388 Pass, 130°C

UV Resistance

ASTM D-4388 Pass

Note: These are typical values and should not be used for specification purposes.



2228 Rubber Mastic Tape

Data Sheet

3M Water Seal Test

Samples were constructed using 2228 tape as a seal between PVC cable jackets and connecting ground wires (3M Cable Grounding Kit 2252). The specimens were thermal cycled in water baths at 25°C and 90°C. The total test time of 336 hours revealed no significant change in insulation resistance. The results exceed requirements listed in UL486D "Standard for Insulated Wire Connectors for Use With Underground Connectors" for insulation resistance (6.0 megohms, section 7.1) and dielectric voltage withstand (2.2kV, 1 minute, section 8.1)

Specification

The tape shall be 1.65mm thick. The tape must be ethylene propylene rubber based and coated with a rubber mastic pressure sensitive adhesive. The tape must be classified for normal service temperatures up to 90°C with allowable short-term exposure up to 130°C.

The tape must be applicable at temperatures of 0°C to 38°C without loss of physical properties. The tape must be classified for use in both indoor and weather exposed outdoor environments.

The tape must not split or crack when exposed to normal operating temperatures and environments. The tape must be compatible with synthetic cable wire insulations. The tape shall not be corrosive to aluminium or copper conductors.

Important Notice

Technical information provided by 3M is based on experience and/or tests believed to be reliable, but their accuracy is not guaranteed and the results may not be relevant to every user's application. For this reason 3M does not accept responsibility or liability, direct or consequential, arising from reliance upon any information provided and the user should determine the suitability of the products for their intended use. Nothing in this statement will be deemed to exclude or restrict 3M's liability for death or personal injury arising from its negligence. All questions of liability relating to 3M products are governed by the seller's terms of sale subject where applicable to the prevailing law. If any goods supplied or processed by or on behalf of 3M prove on inspection to be defective in material or workmanship, 3M will (at its option) replace the same or refund to the Buyer the price paid for the goods or services. Except as set out above, all warranties and conditions, whether express or implied, statutory or otherwise are excluded to the fullest extent permissible at law.

3M and Scotch are trademarks of the 3M Company. Printed in the UK.
© 3M United Kingdom PLC, 2001.

Installation

Scotch 2228 should be applied in half-lapped layers until desired insulation build up is reached. Stretch the tape to $\frac{3}{4}$ of its original width during application for good conformability and to obtain a moisture tight seal.

Scotch 2228 should be overwrapped for mechanical protection with two half-lapped layers of Scotch Brand vinyl electrical tape.

Shelf Life

Scotch 2228 tape has a five year shelf life (from date of manufacture) when stored under the following recommended storage conditions. Store behind present stock in a clean, dry place at a temperature of 70°F (21°C) and 40-50% relative humidity. Good stock rotation is recommended.

Availability

Scotch 2228 Rubber Splicing Tape is available from your local 3M authorised distributor.

