

# Heatshrink Wraparound Repair Sleeves

- Reliable repair of damaged cable sheaths
- Suitable for use with both LV, MV and telecom cable applications
- Thermochromatic paint applied to assist with proper shrinkage



## Stainless Steel Rail Type

Wraparound repair sleeves offer an easy to apply effective solution for the repair of damage to outer sheaths for all cable types.

Used extensively worldwide to provide the outer protection and sealing of telecommunication cables, they are equally useful for power cable joint outer sealing reducing trench excavation.

PART NUMBER	EXP DIA (mm)	REC DIA (mm)	LENGTH (mtr)
SWRS 42/10	42	10	1000mm
SWRS 50/15	50	15	1000mm
SWRS 75/22	75	22	1000mm
SWRS 105/30	105	30	1000mm
SWRS 146/38	146	38	1000mm
SWRS 198/55	188	55	1000mm
SWRS 210/60	210	60	1000mm

Property	Test Method	Performance
Thermal Ageing	168 hrs at 150 + 2 <sup>0</sup> C	Min 13.7MPa
Bursting Strength	Electrode Surface Dia: 6mm Weight 50 + gms Voltage Steps 2kV/20sec	Min 12kV/mm
Spit Resistance	Temp 200+ 2 <sup>0</sup> C Test Time 23 + 3 secs	No splitting
Carbon  Content	Heating Rate 20 <sup>0</sup> C/min	Min 2.6+0.25%
UV Res of Outer Layer	Gas Flow Rate 300cc/min	
Cold Crack Resistance	Test Temp < 40 <sup>0</sup> C	No Cracking
Adhesive Peel Strength	-PE at 23+2 <sup>0</sup> C -PB at 23+2 <sup>0</sup> C	Min 100N/25mm
Shear Strength	At 23+2 <sup>0</sup> C	Min 200N